

Quality : 380830

Indicative properties

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
• Weight	g/m ²	30	ISO 9073-1
• Thickness	mm	0.35	ISO 9073-2

Composition:

• Fibre	50% Viscose, 50% Polyester
• Binding	Chemical
• Finish	
• Colour	White
• Various	

Mechanical Properties:

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
Tensile strength Dry:			
• Machinedirection	N/5 cm	75	ISO 9073-3
• Crossdirection	N/5 cm	12.5	ISO 9073-3
Tensile strength Wet:			
• Machinedirection	N/5 cm	37.5	ISO 9073-3
• Crossdirection	N/5 cm	6	ISO 9073-3
Elongation Dry:			
• Machinedirection	%	10	ISO 9073-3
• Crossdirection	%	10	ISO 9073-3
Elongation Wet:			
• Machinedirection	%	10	DIN 53857
• Crossdirection	%	10	DIN 53857

Properties:

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
• Air Permeability	Ltr/m ² /sec	3500	Din 53887
• Water Permeability	Ltr/m ² /sec	225	Lantor Test method: (14.3 cm H ₂ O)

Standards:

	<i>Unit</i>	<i>Value</i>
• Maximum width	cm	210
• Core diameter	mm	76
• Roll-length	m1	1000
• Packaging		PE Bag

Application: a.o. Filtration

Disclaimer:

The information contained in this document has been compiled in good faith by Lantor B.V., nevertheless no representation or warranty is given as to the accuracy or completeness of the (technical) information provided herein. Lantor B.V. can not be held liable for any damages arising from any (printing) errors or omissions in this information. Lantor B.V. reserves the right to make changes with respect to the information provided at any time without further notice.