

LANTOR CUSTOM - TECHNICAL DATA

Scented Sachet material F51-, 52-,... , F66XXXXXXXXXX

Rev.: 1.2
Date: 24-07-2014

Indicative properties

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
• Weight	g/m ²	100	DIN EN 29073-1
• Thickness	mm	0.70	ISO 9073-2

Composition:

o Fibre	Viscose/PES
o Binding	Chemical
o Finish	PE coating
o Colour	White with printed design on request

Mechanical Properties:

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
Tensile strength:			
o Machine direction	N/5 cm	185	DIN EN 29073-3
o Cross direction	N/5 cm	20	DIN EN 29073-3
Elongation:			
o Machine direction	%	13	DIN EN 29073-3
o Cross direction	%	50	DIN EN 29073-3

Standards :

	<i>Unit</i>	<i>Value</i>
o Maximum width	cm	max. 210
o Core diameter	mm	70/76
o Roll-length	m1	On request
o Packaging		PE Bag

Application: Scented sachet material

This information is provided in good faith, but no warranty is implied.